



TEST REPORT

In Account With LIQUIGUARD TECHNOLOGIES, INC. 2755 E. Oakland Park Blvd, Suite 300 Fort Lauderdale, FL 33306 Attn: Abbas A. Sadriwalla	Date December 11, 2007	Page 1 of 2 Pages
	W.O. Number 35857-1	Specification Not Specified
	P.O.No. Verbal	Received 11-30-07

IDENTIFICATION : The test sample was submitted for testing. The test sample was identified as follows:

IDENTIFICATION

Liquiguard

SPECIFICATION : Not Specified.

REFERENCE : A letter from Liquiguard Technologies, dated 11-27-07.

TESTING : Dielectric Constant and Dissipation Factor.

SUMMARY : The test results, reported herein, are submitted for customer evaluation.

Respectfully submitted,
PACIFIC TESTING LABORATORIES, INC.

Michael Shin
Laboratory Director

DIELECTRIC CONSTANT
AND DISSIPATION FACTOR

REQUIREMENT : Not Specified.

TEST METHOD : The specimen was tested for Dielectric Constant and Dissipation Factor in accordance with ASTM D-150.

CONDITIONING : Tested at a frequency of 100 KHz (at room temperature).

RESULTS : Dielectric Constant and Dissipation Factor test results are as follows:

<u>THICKNESS</u> Inch	<u>TEST</u> <u>TEMP.</u>	<u>FREQUENCY</u> Hertz	<u>DISSIPATION</u> <u>FACTOR</u>	<u>DIELECTRIC</u> <u>CONSTANT</u>
0.0028	R.T.	100 KHz	0.003	2.26

REMARKS : The test results are reported for customer evaluation.