

# CORRUCOTE

CARDBOARD WATERPROOFING & STRENGTHENING



## TECNICAL DATA SHEET

### Chemical Data:

NVW (%)	24% +/- 1%
pH	4.5 - 5.5
Visc. (cps @ 76 deg. F)	1200
Flash Point	>105°F
Chemical Stability	Stable
Polymerization	Does not occur
Storage	60 - 75°F

### Physical Data:

Weight per gallon	8.51 lbs +/- 0.5%
Koenig hardness	20
DFT per coat (approx. 1500 sq. ft./gal.)	8 microns approx.
Good weatherability	
Good chemical resistance	
Excellent adhesion to paper board products	
Appearance - Crystal clear with satin finish	
Resistant to water, beverages, mild acids and oils- Recyclable	

### Cautions:

Do not add water or other liquids to the original material  
Store in closed containers at recommended temperatures  
Keep from freezing and intense heat.